

EPOTEC RD 109**Description**

EPOTEC RD 109 is the monoglycidyl ether of C12-C13 aliphatic alcohol. The primary use of RD 109 is as a reactive diluent for high viscosity epoxy resins. RD 109 is compatible at all concentration and those resins and the blends can be cured with variety of epoxy hardners. As with all monofunctional aliphatic epoxies, increasing level of RD 109 will increase pot life and modify cured properties.

Applications

- Flooring
- Potting and encapsulation
- General purpose adhesives

Typical properties

Property	Test method	Unit	Specification
Appearance	Visual	-	Clear liquid
Color	ASTM D-1544 (89) TEC-AS-P-006	Gardner	Max. 0.5
Epoxy equivalent weight	DIN 16945/4.15B (89) TEC-AS-C-002	g/eq	270 - 315
Viscosity* @ 25°C	JIS K 7233 (86)	cPs	5 - 10

* Brookfield viscosity

Storage

EPOTEC RD 109 should be stored in dry condition and kept closed in original container. Under these conditions, it has a storage life of at least one year.

Handling

Please refer to MSDS for safe handling of EPOTEC RD 109.

Disclaimer

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

For additional information:**ADITYA BIRLA CHEMICALS (EPOXY DIVISION)**

16thFLOOR MAHATHUN PLAZA. 888/160-161 PLOENCHIT ROAD, BANGKOK 10330 THAILAND.

TEL: (662) 2535031-3, 2536882, FAX: (662) 2535030

Website: www.thaiepoxy.com, E-mail: epotec@thaiepoxy.com