



Aditya Birla Chemicals (Thailand) Ltd (Epoxy Division)

**EPOTEC RD 110**

**Description**

EPOTEC RD 110 is the monoglycidyl ether of 2-ethyl hexanol. The primary use of RD 110 is as a reactive diluent for high viscosity epoxy resins. RD 110 is compatible at all concentration and those resins and the blends can be cured with variety of epoxy hardeners. As with all monofunctional aliphatic epoxies, increasing level of RD 110 will increase pot life and modify cured properties.

**Applications**

- Flooring
- Potting and encapsulation
- General purpose adhesives

**Typical properties**

Property	Test method	Unit	Specification
Appearance	Visual	-	Clear liquid
Color	ASTM D-1544 (89) TEC-AS-P-006	Gardner	Max. 0.5
Epoxy equivalent weight	DIN 16945/4.15B (89) TEC-AS-C-002	g/eq	220 - 240
Viscosity* @ 25 °C	JIS K 7233 (86)	cPs	2 - 7
Hydrolysable chlorine	ASTM D-1726 (87) TEC-AS-C-007	wt%	Max. 0.1
Water content	ASTM-D-4017 (90)	wt %	Max. 0.1

\* Brookfield viscosity

**Storage**

EPOTEC RD 110 should be stored in dry condition and kept closed in original container. Under these conditions, it has a storage life of at least one year.

**Handling**

Please refer to MSDS for safe handling of EPOTEC RD 110.

**Disclaimer**

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

**For Additional Information, Please Contact:**

**Aditya Birla Chemicals (Thailand) Ltd. (Epoxy Division)**

Mahatun Plaza Bldg., 16<sup>th</sup> Floor 888/167 Ploenchit Road, Lumpini, Bangkok 10330 Thailand.

Tel: (662) 2535031-3, Fax: (662) 2535030

Web Site: [www.adityabirlachemicals.com](http://www.adityabirlachemicals.com), E-Mail: [epoxymktg@adityabirla.com](mailto:epoxymktg@adityabirla.com)