



**Aditya Birla Chemicals (Thailand) Ltd. (Epoxy Division)**

**EPOTEC YD 136**

### Description

EPOTEC YD 136 is an unmodified semi-solid diglycidyl ether of Bisphenol A. It has higher molecular weight than YD 128.

### Applications

- High solid protective coatings
- Electrical castings
- Adhesives

### Typical properties

Property	Test method	Unit	Specification
Appearance	Visual	-	Clear semi-solid
Color	ASTM-D-1544 (89) TEC-AS-P-006	Gardner	Max. 0.5
Epoxy equivalent weight	DIN-16945/4.15B (89) TEC-AS-C-002	g/eq	290 - 335
Viscosity* @ 25 °C	ASTM-D-4287 (88)	---	A - C

\*Gardener-Holdt viscosity (40 % solids in butyl carbitol)

### Storage

EPOTEC YD 136 resin should be stored in original tightly closed container. Under these conditions, it has a storage life of at least one year.

### Handling

Please refer to MSDS for safe handling of EPOTEC YD 136.

### Disclaimer

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

### For Additional Information, Please Contact:

**Aditya Birla Chemicals (Thailand) Ltd. (Epoxy Division)**

Mahatun Plaza Bldg., 16<sup>th</sup> Floor 888/167 Ploenchit Road, Lumpini, Bangkok 10330 Thailand.

Tel: (662) 2535031-3, Fax: (662) 2535030

Web Site: [www.adityabirlachemicals.com](http://www.adityabirlachemicals.com), E-Mail: [epoxymktg@adityabirla.com](mailto:epoxymktg@adityabirla.com)