

## EPOTEC YD 903TP

### Description

EPOTEC YD 903TP is an unmodified solid epoxy resin, which has medium molecular weight combined with low melt viscosity.

### Typical uses

EPOTEC YD 903TP is mainly used in powder coating formulations for pure epoxy and hybrid epoxy powder paint. It can also be used in solvent based two component coating systems.

### Typical property

Property	Test method	Unit	Specification
Epoxy equivalent weight	DIN 16945/4.15B (89) TEC-AS-C-002	g/eq	700 - 800
Viscosity* @ 25°C (Gardner holdt)	ASTM D-1545 (89)	-	K - P
Color*	ASTM D-1544 (89) TEC-AS-P-006	Gardner	MAX. 0.5
Softening point	ASTM E 28-67 (82)	°C	85 - 95
Melt viscosity @ 150°C	ASTM D-4287 (88)	cPs	2,000 - 3,500

\*40% Solution in Butyl Carbitol

### Packing

EPOTEC YD 903TP is packed & delivered in opaque PE bags weighing 25 kgs net each.

### Storage and handling

EPOTEC YD 903TP resin should be stored in dry condition and kept away from sources of heat. Under these conditions, it has a storage life of at least one year. Acute toxicity and skin irritation of EPOTEC YD 903TP resin is of very low order. However it is advised to use personnel protective equipment to avoid inhalation of dust. It is advisable to take precaution against static electric hazards when emptying bags.

### Disclaimer

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

### For additional information:

#### ADITYA BIRLA CHEMICALS (EPOXY DIVISION)

16<sup>th</sup>FLOOR MAHATHUN PLAZA 888/160-161 PLOENCHIT ROAD, BANGKOK 10330 THAILAND.

TEL: (662) 2535031-3, 2536882, FAX: (662) 2535030

Website: [www.thaiepoxy.com](http://www.thaiepoxy.com), E-mail: [epotec@thaiepoxy.com](mailto:epotec@thaiepoxy.com)