

**EPOTEC YD 984F****Description**

EPOTEC YD 984F is a modified solid epoxy resin containing flow modifier.

**Applications**

- Powder coatings

**Typical properties**

Property	Test method	Unit	Specification
Epoxy equivalent weight	DIN 16945/4.15B (89) TEC-AS-C-002	g/eq	835 - 895
Color*	ASTM D-1544 (89) TEC-AS-P-006	Gardner	Milky white flakes
Softening point	JIS K 7234 (86) ASTM E 28-67 (82)	°C	85 - 100
Melt viscosity @ 150°C	ASTM D 4287 (88)	cPs	1,500 - 4,000

\* 40% Solution in Butyl Carbitol

**Packing**

EPOTEC YD 984F is packed in opaque PE bags weighing 25 kg net each.

**Storage**

EPOTEC YD 984F resin should be stored in dry and cool condition away from sources of heat and ignition in original sealed bags. Under these conditions, it has a storage life of at least one year. Acute toxicity and skin irritation of EPOTEC YD 984F resin is of very low order, However it is advised to use personnel protective equipment to avoid inhalation of dust. It is advised to take precaution against static electric hazards when emptying bags.

**Handling**

Please refer to MSDS for safe handling of EPOTEC YD 984F.

**Disclaimer**

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

**For additional information:****ADITYA BIRLA CHEMICALS (EPOXY DIVISION)**

16<sup>th</sup>FLOOR MAHATHUN PLAZA. 888/160-161 PLOENCHIT ROAD, BANGKOK 10330 THAILAND

TEL: (662) 2535031-3, 2536882, FAX: (662) 2535030

Website: [www.thaiepoxy.com](http://www.thaiepoxy.com), E-mail: [epotec@thaiepoxy.com](mailto:epotec@thaiepoxy.com)