

## EPOTEC YDFM 261

### Description

EPOTEC YDFM 261 is modified Bis A/Bis F blend. This resin has greater crystallization resistance than the normal epoxy resins. The enhancement in the crystallization resistance greatly improves the formulation stability.

### Applications

- Adhesives
- Casting and Tooling
- Civil
- Composite
- Protective coatings
- Potting and Encapsulation

### Typical properties

Property	Test method	Unit	Specification
Appearance	Visual	-	Clear liquid
Color	ASTM-D-1544 (89) TEC-AS-P-006	Gardner	Max. 0.5
Epoxy equivalent weight	DIN 16945/4.15B (89) TEC-AS-C-002	g/eq	174 - 179
Viscosity* @ 25°C	JIS-K-7233 (86)	cPs	4,500 - 6,000

\* Brookfield viscosity

### Storage

EPOTEC YDFM 261 resin should be stored in original tightly closed container, in dry and warm conditions. Under these conditions, it has a storage life of at least one year.

### Handling

Please refer to MSDS for safe handling of EPOTEC YDFM 261.

### Disclaimer

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

### For additional information:

#### ADITYA BIRLA CHEMICALS (EPOXY DIVISION)

16<sup>th</sup>FLOOR MAHATHUN PLAZA. 888/160-161 PLOENCHIT ROAD, BANGKOK 10330 THAILAND

TEL: (662) 2535031-3, 2536882, FAX: (662) 2535030

Website: [www.thaiepoxy.com](http://www.thaiepoxy.com), E-mail: [epotec@thaiepoxy.com](mailto:epotec@thaiepoxy.com)