



Aditya Birla Chemicals (Thailand) Ltd. (Epoxy Division)

EPOTEC YDPN 661

Description

EPOTEC YDPN 661 epoxy novolac resin is a high viscous reaction product of epichlorohydrin and phenol-formaldehyde novolac resin.

EPOTEC YDPN 661 resin is a general-purpose, widely used epoxy novolac resin. This resin has multi-epoxy functionality (~ 2.5). These additional reactive sites produce tightly cross-linked cured systems. This makes YDPN 661 epoxy novolac resin useful for chemical resistance coatings and elevated temperature service applications.

Applications

- Adhesives
- Casting and Tooling
- Composites, Potting and Encapsulation
- Can Coatings
- Marine & Protective Coatings, Photo cure Industrial Coatings

Typical properties

Property	Test method	Unit	Specification
Appearance	Visual	-	Viscous liquid
Color	ASTM- D-1544 (89)	Gardner	Max. 3.0
Epoxy equivalent weight	DIN-16945/4.15B (89)	g/eq	169 - 178
Viscosity* @ 25 °C	JIS-K-7233 (86)	cPs	20,000 - 40,000

* Brookfield viscosity

Storage

EPOTEC YDPN 661 resin should be stored in original container tightly closed, in dry and warm conditions. Under these conditions, it has a storage life of at least one year.

Handling

Please refer to MSDS for safe handling of EPOTEC YDPN 661.

Disclaimer

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

For Additional Information, Please Contact:

Aditya Birla Chemicals (Thailand) Ltd. (Epoxy Division)

Mahatun Plaza Bldg., 16th Floor 888/167 Ploenchit Road, Lumpini, Bangkok 10330 Thailand.

Tel: (662) 2535031-3, Fax: (662) 2535030.

Web Site: www.adityabirlachemicals.com, E-Mail: epoxymktg@adityabirla.com