

EPOTEC YDR 300

Description

EPOTEC YDR 300 is a elastomer modified diglycidyl ether of Bisphenol A. EPOTEC YDR 300 is used to modify conventional epoxy resins to impart flexibility, improve adhesion and fatigue resistance.

Applications

- High performance adhesives
- Composites
- Electrical castings
- Solvent based coatings

Typical properties

Property	Test method	Unit	Specification
Epoxy equivalent weight	DIN 16945/4.15B (89) TEC-AS-C-002	g/eq	330 - 360
Viscosity* @25°C	JIS K 7233 (86)	cPs	150,000 - 300,000
Colour	ASTM D-1544 (89) TEC-AS-P-006	Gardner	Max. 12

*Brookfield viscosity

Storage

EPOTEC YDR 300 resin should be stored in dry and cool condition in original tightly closed container. Under these conditions, it has a storage life of at least one year.

Handling

Please refer to MSDS for safe handling of the EPOTEC YDR 300.

Disclaimer

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

For additional information

ADITYA BIRLA CHEMICALS (EPOXY DIVISION)

16thFLOOR MAHATHUN PLAZA 888/160-161 PLOENCHIT ROAD, BANGKOK 10330 THAILAND

TEL: (662) 2535031-3, 2536882, FAX: (662) 2535030.

Website: www.thaiepoxy.com, E-mail: epotec@thaiepoxy.com